

# DURALAC

## Epoxy Concrete Primer Sealer 1010

**Description:**

DURALAC Epoxy Concrete Primer Sealer 1010 is a clear high quality two-component sealer, based on epoxy resins and polyamide activator, designed to penetrate and seal concrete surfaces.

**Area of Use:**

DURALAC Epoxy Concrete Primer Sealer 1010 is used as a primer for parking decks, industrial floors, food industry floors, etc...under DURALAC Epoxy Concrete Top Coat 1000 Series, as a dust proofer and substrate hardener binder if not recoated and as a glaze protective top coat.

**Technical Data:**

Specific Gravity	: 1,08 ± 0,02	Mixing Ratio by Vol.	: 1 Part (base A-Resins) to 1 Part (base B-Activator) (Pre-measured)
Viscosity	: 85 KU	Induction Time	: ≥ 30 min
Solid by volume	: 37 ± 0.5%	Pot Life	: 7 hours @ 25 °C
Finish	: Clear & Glossy	Mode of application	: Roller; Brush; Squeegee & airless spray
Coverage	: 12,5m <sup>2</sup> /liter@80 microns wft.	Thinning	: 10-40% upon need
Flash Point	: ≥ 25 °C	Thinner	: <b>X 279 Thinner.</b>
Dry to touch	: 50-70 min @ 25 °C	Cleaning of tools	: <b>X 275 Thinner.</b>
Dry to recoat	: 5-7 hours @ 25 °C	Scrub Resistance	: High.
Full Curing	: 7 days @ 25 °C	Solvent Resistance	: Good.
Storage	: 2 years from production date	Water Resistance	: Excellent.
		Chemical Resistance	: Excellent.

**Surfaces Preparation:**

The substrate to be primed should be suitably dry, clean, free from loose material, dust, grease, oil and any other contamination. Treat any areas affected by mould, lichens, algae and moss with fungicidal solution. Confirm that the correct surface preparation and pre-treatment is carried out.

**New Surfaces:**

Clean the surface from laitance, dust, dirt and loose particles. Then apply one coat of DURALAC Epoxy Concrete Primer Sealer 1010.

**Repaintings:**

For previously epoxy coated surfaces, grind with mechanical fine graded sand paper, wash with etching solution, rinse thoroughly with water to remove all residues. Allow to dry well, then use one coat of DURALAC Epoxy Concrete Primer Sealer 1010.

**System Information:**

Stir thoroughly before use. Add all the hardener to the resin in a ratio of 1 part (hardener 1010-1) to 1 part (resin 1010) and mix for 2-3 minutes.

Standard packages are in pre-measured kits and should be mixed as supplied. We recommend that the kits not be broken down unless suitable weighing equipment is available.

Allow mixed material to sweat-in for 30 minutes before starting application. All epoxy coatings and urethanes are compatible for use as a topcoat for (1010 Epoxy concrete primer sealer) as well as multiple coats of this product.

Before top coating, make sure the previous coat has tacked off.

**Painting Information:**

DURALAC Epoxy Concrete Primer Sealer (1010).

1 coat (Primer)

DURALAC Epoxy Universal Top Coat

2 coats (Finish Coat)

**Packing:**

Available in USG, Component A (resins)=1.67 liters to Component B (activator)=1.93 liters.  
20 liters Pail, Component A (resins)= 9,3 liters to Component B (activator)=10,7 liters.

**General Information:**

- Do not apply when the air or substrate temperatures are likely to fall below 10 °C or when the relative humidity is above 80% during application or the drying period.
- Substrate to be treated must not exceed 5% by weight moisture content.
- Under normal conditions this product will remain usable for up to two years if stored correctly and unopened.
- Store in a cool, dry and ventilated place. Keep container closed when not in use.
- All cited parameters must be considered as guidelines only.

**Health and Safety:**

- When preparing or painting all surfaces avoid the inhalation of dust and paint mist.
- Ensure good ventilation and use mask and safety gloves while applying.
- Avoid skin contact, spoiled skin should immediately be washed.
- In case of eye contact, flush with plenty of water and consult a doctor.
- If accidentally swallowed seek medical attention immediately.
- Smoking, eating and drinking must be prohibited in the application area.
- Keep away from food, children and animals.
- Do not empty into sewer, watercourses or access routes to septic tanks.

**For more information on safety hazards and precautions, please refer to the product MSDS.**

The line manufacturing process is batch checked, ensuring traceability in the event of any incident. The quality system employed includes the actual design of every item and the controls in its fabrication, both of the raw materials used to ensure uniformity of manufacture and the end product obtained.

**Disclaimer:**

For proper use and correct application of the product, a prior reading of the technical features is indispensable. The data provided in this technical specifications was obtained to the best of our knowledge under normal laboratory conditions and on standardised bases, and may vary depending on the working conditions. The working conditions of the users are at all times beyond our control, we cannot guarantee anything but the quality of the product itself. The product must not be used for purpose other than those specified.

We have a technical-commercial team at your disposal to help you with any queries.

Due to standards and specification evolution, the company reserves the right to change the given data without prior notification.

**Universal Paints Manufacturing Co. Ltd.** Industrial City, Phase 03, Kingdom of Saudi Arabia  
Tel: +966 2 2686999 Fax: +966 2 6389680 Po.Box: 16945, Jeddah: 21474

